

Product Data Sheet

Product	Alumakote (also known as Bituminous Aluminium)
Product Code	636
Description	This product is fairly high lustre paint, having good durability and is mainly intended for use on zinc and concrete roofs, contains bituminous emulsion.
Composition	Mixture of Alkyd and hard resin as well as Bitumen

Physical Properties

Colour	Aluminium
Appearance	Lustre
Viscosity	50 seconds (FC 4)
Shelf Life	approximately 12 months
Storage Conditions	below 30°
Pack Size	5ℓ, 20ℓ

Application Properties

Method	brush or roller
Volume Solids (Typical)	27%
Recommended Average DFT in microns	25
Theoretical Coverage (m² / ℓ)	8 - 10
Wet Film Thickness in microns	100 microns
Recommended No of Coats	one or two depending requirement
Drying Time at 25°C	6 hours (touch dry) 16 hours (hard dry)
Overcoating Time at 25°C	overnight
Thinning	ready for use
Cleaning Solvent	QD Thinners
Recommended System	Apply directly on to dust free malthoid bituminous membrane, steel or concrete surfaces and zinc roofs

Precaution

Flashpoint	11°C
Toxicity	use in well ventilated areas

Note

THIS PRODUCT IS LEAD FREE

No guarantee is implied by the recommendations contained herein since the data sheet is issued for information purposes only. Method of application on surface, cleanliness and conditions of use etc. are beyond our control.