

Product Data Sheet

| | |
|---------------------|---|
| Product | Chlorinated Rubber Enamel |
| Product Code | 1200 / 1201 / 1210 |
| Description | A general purpose Chlorinated Enamel for use where high water and acid resistance is required – swimming pool paint |
| Composition | Chlorinated Rubber |

Physical Properties

| | |
|---------------------------|------------------------------|
| Colour | White / Black / Grey / Blue |
| Appearance | gloss |
| Viscosity | 60 seconds (FC 4) |
| Shelf Life | approximately 10 – 15 months |
| Storage Conditions | below 30°C |
| Pack Size | 5ℓ |

Application Properties

| | |
|---|---|
| Method | roller, brush or spray |
| Volume Solids (Typical) | 20% |
| Recommended Average DFT in microns | 25 |
| Theoretical Coverage (m² / ℓ) | 6 - 8 |
| Wet Film Thickness in microns | 125 microns |
| Recommended No of Coats | two or three |
| Drying Time at 25°C | 45 minutes (touch dry) 4 hours (hard dry) |
| Overcoating Time at 25°C | 18 hours |
| Thinning | up to 10% with Chlorinated Rubber Thinners |
| Cleaning Solvent | Chlorinated Rubber Thinners |
| Recommended System | Apply directly on to new, clean concrete surfaces or steel surfaces primed with Etch Primer |

Precaution

| | |
|-------------------|--|
| Flashpoint | Above 20°C |
| Toxicity | apply only in well ventilated areas do not apply in direct sunshine, apply early morning and late afternoon |

Note

THIS PRODUCT IS LEAD FREE

No guarantee is implied by the recommendations contained herein since the data sheet is issued for information purposes only. Method of application on surface, cleanliness and conditions of use etc. are beyond our control.