

## Product Data Sheet

|                     |   |
|---------------------|---|
| <b>Product</b>      | NC Lacquer Clear  |
| <b>Product Code</b> | 1190  |
| <b>Description</b>  | A protective and decorative coating for wooden surfaces where a high gloss finish is required |
| <b>Composition</b>  | Nitrocellulose  |

### Physical Properties

|                           |                        |
|---------------------------|------------------------|
| <b>Colour</b>             | Clear                  |
| <b>Appearance</b>         | High gloss or suede    |
| <b>Viscosity</b>          | 40 – 50 seconds (FC-4) |
| <b>Shelf Life</b>         | 8 – 12 months          |
| <b>Storage Conditions</b> | normal                 |
| <b>Pack Size</b>          | 5ℓ, 20ℓ                |

### Application Properties

|   |   |
|---|---|
| <b>Method</b>                                   | brush or spray                                    |
| <b>Volume Solids (Typical)</b>                  | 27%   |
| <b>Recommended Average DFT in microns</b>       | 25 microns  |
| <b>Theoretical Coverage (m<sup>2</sup> / ℓ)</b> | 10 - 12   |
| <b>Wet Film Thickness in microns</b>            | 90  |
| <b>Recommended No of Coats</b>                  | one or two depending on surface                   |
| <b>Drying Time at 25°C</b>                      | 15 minutes (touch dry)<br>2 hours (hard dry)      |
| <b>Overcoating Time at 25°C</b>                 | 6 hours   |
| <b>Thinning</b>                                 | up to 20% with Lacquer Thinners                   |
| <b>Cleaning Solvent</b>                         | Lacquer Thinners                                  |
| <b>Recommended System</b>                       | For use as a finishing coat on any wooden surface |

### Precaution

|                   |                              |
|-------------------|------------------------------|
| <b>Flashpoint</b> | Below 10°                    |
| <b>Toxicity</b>   | use in well ventilated areas |

### Note

**THIS PRODUCT IS LEAD FREE**

**No guarantee is implied by the recommendations contained herein since the data sheet is issued for information purposes only. Method of application on surface, cleanliness and conditions of use etc. are beyond our control.**