

Product Data Sheet

Product	Temporary Protective Coating
Product Code	1050
Description	A temporary protective coating to use on any steel surface to prevent rust
Composition	Oleo Resinous

Physical Properties

Colour	Clear
Appearance	gloss
Viscosity	20 – 25 seconds (FC4)
Shelf Life	approximately 12 months
Storage Conditions	normal
Pack Size	5ℓ, 20ℓ

Application Properties

Method	brush, spray or dipping
Volume Solids (Typical)	40%
Recommended Average DFT in microns	25
Theoretical Coverage (m² / ℓ)	12 - 16
Wet Film Thickness in microns	60 microns
Recommended No of Coats	depending on DFT
Drying Time at 25°C	20 minutes (touch dry) 2 hours (hard dry)
Overcoating Time at 25°C	4 hours
Thinning	ready for use
Cleaning Solvent	QD Thinners
Recommended System	Use as a temporary protective coating for any prepared, clean steel surfaces

Precaution

Flashpoint	10°C
Toxicity	normal when used in well ventilated areas

Note

THIS PRODUCT IS LEAD FREE

No guarantee is implied by the recommendations contained herein since the data sheet is issued for information purposes only. Method of application on surface, cleanliness and conditions of use etc. are beyond our control.